

BASF Ultraform® Z2320 003 POM

Description: Is a POM, rapidly solidifying grade for applications with exceptional demands on flowability.
Information provided by BASF

Physical Properties	Metric	English	Comments
Bulk Density	0.850 g/cc	0.0307 lb/in ³	
Density	1.40 g/cc	0.0506 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23°C; 50% RH; ISO 62
Water Absorption at Saturation	0.80 %	0.80 %	ISO 62
Linear Mold Shrinkage, Flow	0.020 cm/cm	0.020 in/in	ISO 2577
Linear Mold Shrinkage, Transverse	0.021 cm/cm	0.021 in/in	ISO 2577
Melt Flow	58.8 g/10 min @Load 2.16 kg, Temperature 190 °C	58.8 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	150 MPa @Load 36.5 kg, Time 30.0 sec	21800 psi @Load 80.5 lb, Time 0.00833 hour	ISO 2039-1
Tensile Strength, Yield	65.0 MPa	9430 psi	50 mm/min; ISO 527-2
Elongation at Break	20 %	20 %	Nominal, 50mm/min; ISO 527-2
Elongation at Yield	7.0 %	7.0 %	ISO 527-2
Modulus of Elasticity	2.80 GPa	406 ksi	ISO 527-2
Charpy Impact Unnotched	13.0 J/cm ² @Temperature -30.0 °C	61.9 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eU
	13.0 J/cm ² @Temperature 23.0 °C	61.9 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eU
Charpy Impact, Notched	0.450 J/cm ² @Temperature -30.0 °C	2.14 ft-lb/in ² @Temperature -22.0 °F	ISO 179/1eA
	0.550 J/cm ² @Temperature 23.0 °C	2.62 ft-lb/in ² @Temperature 73.4 °F	ISO 179/1eA
Tensile Creep Modulus, 1000 hours	1350 MPa	196000 psi	ISO 899-1

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	IEC 60093
Dielectric Constant	3.8 @Frequency 1e+6 Hz	3.8 @Frequency 1e+6 Hz	IEC 60250
	3.8 @Frequency 100 Hz	3.8 @Frequency 100 Hz	IEC 60250
Dielectric Strength	40.0 kV/mm	1020 kV/in	IEC 60243-1
Dissipation Factor	0.0010 @Frequency 100 Hz	0.0010 @Frequency 100 Hz	IEC 60250
	0.0050 @Frequency 1e+6 Hz	0.0050 @Frequency 1e+6 Hz	IEC 60250
Comparative Tracking Index	600 V	600 V	Test solution A; IEC 60112
	600 V	600 V	Test solution B; IEC 60112