

Chi Mei® PA-757

High gloss, medium impact

No vendors are listed for this material. Please click [here](#) if you are a supplier and would like information on how to add your listing to this material.

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	ISO 1183
Linear Mold Shrinkage	0.0030 - 0.0070 cm/cm	0.0030 - 0.0070 in/in	ASTM D955
Melt Flow	1.8 g/10 min @Load 5.00 kg, Temperature 200 °C	1.8 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238
	22 g/10 min @Load 10.0 kg, Temperature 220 °C	22 g/10 min @Load 22.0 lb, Temperature 428 °F	ISO-1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	116	116	ASTM D785
Ball Indentation Hardness	110 MPa	16000 psi	H358/30; ISO 2039-1
Tensile Strength at Break	37.0 MPa	5370 psi	50 mm/min; ISO 527
Tensile Strength, Yield	54.0 MPa	7830 psi	50 mm/min; ISO 527
Elongation at Break	20 %	20 %	50 mm/min; ISO 527
Flexural Strength	76.0 MPa	11000 psi	2 mm/min; ISO 178
Flexural Modulus	2.20 GPa	319 ksi	2 mm/min; ISO 178
Izod Impact, Notched	1.83 J/cm @Thickness 6.35 mm	3.43 ft-lb/in @Thickness 0.250 in	ASTM D256
	2.05 J/cm @Thickness 3.17 mm	3.84 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Notched (ISO)	14.0 kJ/m ²	6.66 ft-lb/in ²	ISO 180/1A
Izod Impact, Unnotched (ISO)	NB	NB	ISO 180/1C
Charpy Impact Unnotched	NB	NB	ISO 179
Charpy Impact, Notched	1.50 J/cm ²	7.14 ft-lb/in ²	ISO 179
Impact	11	11	Impact Flexural Test Notched (KJ/m ²)
	NB	NB	Impact Flexural Test Unnotched (KJ/m ²)

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	88.0 °C	190 °F	unannealed; ISO 75
	98.0 °C	208 °F	annealed; ISO 75
Vicat Softening Point	100 °C @Load 5.00 kg	212 °F @Load 11.0 lb	50°C/hr; ISO 306
	101 °C @Load 5.00 kg	214 °F @Load 11.0 lb	120°C/hr; ISO 306
	104 °C @Load 1.00 kg	219 °F @Load 2.20 lb	50°C/hr; ISO 306
	105 °C @Load 1.00 kg	221 °F @Load 2.20 lb	120°C/hr; ISO 306
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0625 in	UL 94