

Chevron Phillips Marlex® 1007

This autoclave LDPE homopolymer is tailored for applications that require:

- Excellent flexibility
- Good flow

Physical Properties	Metric	English	Comments
Density	0.917 g/cc	0.0331 lb/in ³	ASTM D1505

Melt Flow	7.0 g/10 min @Load 2.16 kg, Temperature 190 °C	7.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D 1238
-----------	--	--	-------------

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	47	47	ASTM D2240

Tensile Strength, Yield	9.00 MPa	1310 psi	2 in/min, Type IV bar; ASTM D638
-------------------------	----------	----------	-------------------------------------

Elongation at Break	600 %	600 %	2 in/min, Type IV bar; ASTM D638
---------------------	-------	-------	-------------------------------------

Flexural Modulus	0.200 GPa	29.0 ksi	Tangent - 16:1 span:depth, 0.5 in/min; ASTM D790
------------------	-----------	----------	--

Thermal Properties	Metric	English	Comments
Vicat Softening Point	87.0 °C	189 °F	Loading 1, Rate A; ASTM D1525

Brittleness Temperature	-66.0 °C	-86.8 °F	Type A, Type I specimen; ASTM D746
-------------------------	----------	----------	---------------------------------------

Compliance Properties	Metric	English	Comments
FDA	Yes	Yes	See notes for details.