

Chevron Phillips Marlex® 1122B

This autoclave LDPE homopolymer is tailored for applications that require:

- Excellent flexibility
- Moderate flow

Physical Properties	Metric	English	Comments
Density	0.920 g/cc	0.0332 lb/in ³	ASTM D1505

Melt Flow	2.1 g/10 min @Load 2.16 kg, Temperature 190 °C	2.1 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D 1238
-----------	--	--	-------------

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	50	50	ASTM D2240

Tensile Strength, Ultimate	13.8 MPa	2000 psi	ASTM D638
----------------------------	----------	----------	-----------

Tensile Strength, Yield	10.0 MPa	1450 psi	2 in/min, Type IV bar; ASTM D638
-------------------------	----------	----------	-------------------------------------

Elongation at Break	500 %	500 %	2 in/min, Type IV bar; ASTM D638
---------------------	-------	-------	-------------------------------------

Flexural Modulus	0.270 GPa	39.2 ksi	Tangent - 16:1 span:depth, 0.5 in/min; ASTM D790
------------------	-----------	----------	--

Thermal Properties	Metric	English	Comments
Vicat Softening Point	93.0 °C	199 °F	Loading 1, Rate A; ASTM D1525

Brittleness Temperature	<= -75.0 °C	<= -103 °F	Type A, Type I specimen; ASTM D746
-------------------------	-------------	------------	---------------------------------------

Compliance Properties	Metric	English	Comments
FDA	Yes	Yes	See notes for details.