

Chi Mei Wonderlite[®] PC-110L

Head Lamp

Vendors: No vendors are listed for this material. Please click [here](#) if you are a supplier and would like information on how to add your listing to this material.

Physical Properties	Metric	English	Comments
---------------------	--------	---------	----------

Density	1.20 g/cc	0.0434 lb/in ³	ISO 1183
---------	-----------	---------------------------	----------

Melt Flow	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	Melt Volume Rate (ml/10 min); ISO 1133
-----------	---	---	--

Mechanical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Ball Indentation Hardness	100 MPa	14500 psi	H358/30; ISO 2039-1
---------------------------	---------	-----------	---------------------

Tensile Strength at Break	75.0 MPa	10900 psi	50 mm/min; ISO 527
---------------------------	----------	-----------	--------------------

Tensile Strength, Yield	65.0 MPa	9430 psi	50 mm/min; ISO 527
-------------------------	----------	----------	--------------------

Elongation at Break	120 %	120 %	50 mm/min; ISO 527
---------------------	-------	-------	--------------------

Flexural Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
-------------------	----------	-----------	-------------------

Flexural Modulus	2.40 GPa	348 ksi	2 mm/min; ISO 178
------------------	----------	---------	-------------------

Izod Impact, Notched (ISO)	80.0 kJ/m ²	38.1 ft-lb/in ²	ISO 180/4A
----------------------------	------------------------	----------------------------	------------

Charpy Impact, Notched	7.50 J/cm ²	35.7 ft-lb/in ²	ISO 179
------------------------	------------------------	----------------------------	---------

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Deflection Temperature at 1.8 MPa (264 psi)	127 °C	261 °F	annealed; ISO 75
--	--------	--------	------------------

	142 °C	288 °F	unannealed; ISO 75
--	--------	--------	--------------------

Vicat Softening Point	143 °C @Load 5.00 kg	289 °F @Load 11.0 lb	50°C/hr; ISO 306
-----------------------	-------------------------	-------------------------	------------------

	148 °C @Load 1.00 kg	298 °F @Load 2.20 lb	50°C/hr; ISO 306
--	-------------------------	-------------------------	------------------

Flammability, UL94	V-2 @Thickness 1.50 mm	V-2 @Thickness 0.0590 in	
--------------------	---------------------------	-----------------------------	--