

Chi Mei Wonderlite® PC-122

High Flow

Vendors:

No vendors are listed for this material. Please click [here](#) if you are a supplier and would like information on how to add your listing to this material.

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in³	ISO 1183

Melt Flow	22 g/10 min @Load 1.20 kg, Temperature 300 °C	22 g/10 min @Load 2.65 lb, Temperature 572 °F	Melt Volume Rate (ml/10 min); ISO 1133
-----------	---	---	--

Mechanical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Ball Indentation Hardness	102 MPa	14800 psi	H358/30; ISO 2039-1
Tensile Strength at Break	70.0 MPa	10200 psi	50 mm/min; ISO 527
Tensile Strength, Yield	63.0 MPa	9140 psi	50 mm/min; ISO 527
Elongation at Break	120 %	120 %	50 mm/min; ISO 527
Flexural Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
Flexural Modulus	2.40 GPa	348 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	70.0 kJ/m²	33.3 ft-lb/in²	ISO 180/4A
Charpy Impact, Notched	6.00 J/cm²	28.6 ft-lb/in²	ISO 179

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Deflection Temperature at 1.8 MPa (264 psi)	128 °C	262 °F	annealed; ISO 75
	143 °C	289 °F	unannealed; ISO 75
Vicat Softening Point	145 °C @Load 5.00 kg	293 °F @Load 11.0 lb	50°C/hr; ISO 306
	150 °C @Load 1.00 kg	302 °F @Load 2.20 lb	50°C/hr; ISO 306

Flammability, UL94	V-2 @Thickness 3.00 mm	V-2 @Thickness 0.118 in	
--------------------	---------------------------	----------------------------	--