

Formosa TAIRIREX® GP5250

Features: General purpose grade

Application: Toys、Lampshade、Containers、Cosmetic bottles、Food container、Media packaging、Stationery、Housewares application
 、Audio tapes、General purpose

Physical property		Standard	Value	Unit
Density	23°C	ASTM D792	1.04	g/cm ³
Melt Index	200°C 5kg	ASTM D1238	6.5	
Monomer Content			700	ppm
Mechanical behavior		Standard	Value	Unit
Tensile Modulus	23°C	ASTM D638	31000	kg/cm ²
Tensile Modulus	23°C	ASTM D638	3036	MPa
Tensile Strength	23°C	ASTM D638	430	kg/cm ²
Tensile Strength	23°C	ASTM D638	40	MPa
Elongation	23°C	ASTM D638	2	%
Flexural Strength	23°C	ASTM D790	850	kg/cm ²
Flexural Strength	23°C	ASTM D790	84	MPa
Flexural Modulus	23°C	ASTM D790	32000	kg/cm ²
Flexural Modulus	23°C	ASTM D790	3136	MPa
Izod Notch Impact	23°C 6.4mm	ASTM D256	1.4	kg-cm/cm
Izod Notch Impact	23°C 6.4mm	ASTM D256	14	J/m
Thermal		Standard	Value	Unit
HDT	Annealed 3.2mm Annealed at 80°C for 2 hours	ASTM D648	86	°C
Vicat Softening Temperature Annealed 3.2mm Annealed at 80°C for 2 hours		ASTM D1525	95	°C
Flammability		Standard	Value	Unit
Flame Rating	All Color 1.5~1.7mm	UL94	HB	
UL		Standard	Value	Unit
UL FlameRating	ALL 1.5~1.7mm	UL94	HB	
HWI	ALL 1.5~1.7mm	UL 746A	3	PLC
HAI	ALL 1.5~1.7mm	UL 746A	0	PLC
RTI Elec	ALL 1.5~1.7mm	UL 746B	50	°C
RTI Elec	ALL 3.0mm	UL 746B	50	°C
RTI Imp	ALL 1.5~1.7mm	UL 746B	50	°C
RTI Imp	ALL 3.0mm	UL 746B	50	°C
RTI Str	ALL 1.5~1.7mm	UL 746B	50	°C
RTI Str	ALL 3.0mm	UL 746B	50	°C
Comparative Tracking Index		IEC 60112	1	PLC
HVTR		UL 746A	1	PLC
Arc Resistance		ASTM D495	6	PLC