

Formosa TAIRIREX[®] GP535N

Features: General purpose grade、Low monomer residue、High heat resistance

Application: Toys、Home Appliances Applications、Refrigerator sheet、Lampshade、Food container、Disposable tableware、Composites、General purpose

Physical property		Standard	Value	Unit
Density	23°C	ASTM D792	1.04	g/cm ³
Melt Index	200°C 5kg	ASTM D1238	3.5	g/10min
Monomer Content			700	ppm
Mechanical behavior		Standard	Value	Unit
Tensile Modulus	23°C	ASTM D638	32000	kg/cm ²
Tensile Modulus	23°C	ASTM D638	3136	MPa
Tensile Strength	23°C	ASTM D638	450	kg/cm ²
Tensile Strength	23°C	ASTM D638	43	MPa
Elongation	23°C	ASTM D638	2	%
Flexural Strength	23°C	ASTM D790	890	kg/cm ²
Flexural Strength	23°C	ASTM D790	88	MPa
Flexural Modulus	23°C	ASTM D790	32000	kg/cm ²
Flexural Modulus	23°C	ASTM D790	3136	MPa
Izod Notch Impact	23°C 6.4mm	ASTM D256	1.5	kg-cm/cm
Izod Notch Impact	23°C 6.4mm	ASTM D256	15	J/m
Thermal		Standard	Value	Unit
HDT	Annealed 3.2mm Annealed at 80°C for 2 hours	ASTM D648	93	°C
Vicat Softening Temperature Annealed 3.2mm Annealed at 80°C for 2 hours		ASTM D1525	98	°C
Flammability		Standard	Value	Unit
Flame Rating	All Color 1.5~1.7mm	UL94	HB	