

Mitsubishi Iupilon[®] S2000UR

Information provided by US distributor Polymer Technology and Services, LLC (PTS).

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ASTM D792
Water Absorption	0.25 %	0.25 %	24 hours at 73°F
Linear Mold Shrinkage	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	ASTM D955
Melt Flow	9.5 g/10 min @Load 1.20 kg, Temperature 300 °C	9.5 g/10 min @Load 2.65 lb, Temperature 572 °F	
Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	65	65	ASTM D785
Hardness, Rockwell R	123	123	ASTM D785
Tensile Strength, Ultimate	66.5 MPa @Thickness 3.17 mm	9650 psi @Thickness 0.125 in	
Tensile Strength, Yield	60.3 MPa @Thickness 3.17 mm	8750 psi @Thickness 0.125 in	
Elongation at Break	120 % @Thickness 3.17 mm	120 % @Thickness 0.125 in	
Flexural Yield Strength	87.1 MPa @Thickness 3.17 mm	12600 psi @Thickness 0.125 in	
Flexural Modulus	2.25 GPa @Thickness 3.17 mm	326 ksi @Thickness 0.125 in	
Izod Impact, Notched	9.45 J/cm @Thickness 3.17 mm	17.7 ft-lb/in @Thickness 0.125 in	
Thermal Properties	Metric	English	Comments
CTE, linear	117 µm/m-°C @Temperature 20.0 °C	65.0 µin/in-°F @Temperature 68.0 °F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	140 °C	284 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	128 °C	262 °F	ASTM D648
Flammability, UL94	V-2 @Thickness 1.59 mm	V-2 @Thickness 0.0625 in	
Optical Properties	Metric	English	Comments
Refractive Index	1.585 @Wavelength 589.3 nm	1.585 @Wavelength 589.3 nm	nD
Transmission, Visible	87 %	87 %	
Processing Properties	Metric	English	Comments
Rear Barrel Temperature	266 - 277 °C	510 - 530 °F	

Middle Barrel Temperature	271 - 282 °C	520 - 540 °F	
Front Barrel Temperature	282 - 299 °C	540 - 570 °F	
Nozzle Temperature	277 - 304 °C	530 - 580 °F	
Melt Temperature	288 - 316 °C	550 - 600 °F	
Mold Temperature	71.1 - 93.3 °C	160 - 200 °F	
Drying Temperature	121 °C	250 °F	
Dry Time	3 - 4 hour	3 - 4 hour	48 hours max.
Injection Pressure	82.7 - 124 MPa	12000 - 18000 psi	
Back Pressure	0.345 - 1.38 MPa	50.0 - 200 psi	
Clamp Pressure	27.6 - 68.9 MPa	4000 - 10000 psi	
Shot Size	40 - 60 %	40 - 60 %	
Screw Speed	40 - 70 rpm	40 - 70 rpm	

Descriptive Properties

Injection Speed- Edge Gate	Slow to Medium
Injection Speed- Tab Gate	Medium to Fast
Injection Speed- Tunnel Gate	Fast