

Mitsubishi Iupilon[®] S3000UR

Information provided by US distributor Polymer Technology and Services, LLC (PTS).

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	ASTM D792

Water Absorption	0.25 %	0.25 %	24 hours at 73°F
------------------	--------	--------	------------------

Linear Mold Shrinkage	0.0050 - 0.0080 cm/cm	0.0050 - 0.0080 in/in	ASTM D955
-----------------------	-----------------------	-----------------------	-----------

Melt Flow	16.5 g/10 min @Load 1.20 kg, Temperature 300 °C	16.5 g/10 min @Load 2.65 lb, Temperature 572 °F	
-----------	---	---	--

Mechanical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Hardness, Rockwell M	65	65	ASTM D785
----------------------	----	----	-----------

Hardness, Rockwell R	122	122	ASTM D785
----------------------	-----	-----	-----------

Tensile Strength, Ultimate	66.5 MPa @Thickness 3.17 mm	9650 psi @Thickness 0.125 in	
----------------------------	--------------------------------	---------------------------------	--

Tensile Strength, Yield	60.3 MPa @Thickness 3.17 mm	8750 psi @Thickness 0.125 in	
-------------------------	--------------------------------	---------------------------------	--

Elongation at Break	120 % @Thickness 3.17 mm	120 % @Thickness 0.125 in	
---------------------	-----------------------------	------------------------------	--

Flexural Yield Strength	85.1 MPa @Thickness 3.17 mm	12300 psi @Thickness 0.125 in	
-------------------------	--------------------------------	----------------------------------	--

Flexural Modulus	2.25 GPa @Thickness 3.17 mm	326 ksi @Thickness 0.125 in	
------------------	--------------------------------	--------------------------------	--

Izod Impact, Notched	8.81 J/cm @Thickness 3.17 mm	16.5 ft-lb/in @Thickness 0.125 in	
----------------------	---------------------------------	--------------------------------------	--

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

CTE, linear	117 µm/m-°C @Temperature 20.0 °C	65.0 µin/in-°F @Temperature 68.0 °F	ASTM D696
-------------	-------------------------------------	--	-----------

Deflection Temperature at 0.46 MPa (66 psi)	140 °C	284 °F	ASTM D648
---	--------	--------	-----------

Deflection Temperature at 1.8 MPa (264 psi)	128 °C	262 °F	ASTM D648
---	--------	--------	-----------

Flammability, UL94	V-2 @Thickness 1.59 mm	V-2 @Thickness 0.0625 in	
--------------------	---------------------------	-----------------------------	--

--	--	--	--

Optical Properties	Metric	English	Comments
--------------------	--------	---------	----------

Refractive Index	1.585 @Wavelength 589.3 nm	1.585 @Wavelength 589.3 nm	nD
Transmission, Visible	87 %	87 %	

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	249 - 271 °C	480 - 520 °F	
Middle Barrel Temperature	260 - 271 °C	500 - 520 °F	
Front Barrel Temperature	271 - 288 °C	520 - 550 °F	
Nozzle Temperature	266 - 282 °C	510 - 540 °F	
Melt Temperature	277 - 293 °C	530 - 560 °F	
Mold Temperature	71.1 - 93.3 °C	160 - 200 °F	
Drying Temperature	121 °C	250 °F	
Dry Time	3 - 4 hour	3 - 4 hour	48 hours max.
Injection Pressure	68.9 - 124 MPa	10000 - 18000 psi	
Back Pressure	0.345 - 1.38 MPa	50.0 - 200 psi	
Clamp Pressure	27.6 - 68.9 MPa	4000 - 10000 psi	
Shot Size	40 - 60 %	40 - 60 %	
Screw Speed	40 - 70 rpm	40 - 70 rpm	

Descriptive Properties	
Injection Speed- Edge Gate	Slow to Medium
Injection Speed- Tab Gate	Medium to Fast
Injection Speed- Tunnel Gate	Fast