

SABIC LEXAN™ 104

UL rated HB. 200 series recommended when V-2 rating required. 7.0 MFR, for thicker sections without sinks. FDA food contact compliant in limited colors. Effective January 15th, 2007 this grade will no longer be supported with biocompatibility information and should not be used for medical applications which require biocompatibility. Alternative grade HP6NR. Information provided by SABIC

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
	1.20 g/cc	1.20 g/cc	ASTM D792
Density	1.19 g/cc	0.0430 lb/in ³	ASTM D792
Water Absorption	0.15 %	0.15 %	24 hours; ASTM D570
Moisture Absorption at Equilibrium	0.35 %	0.35 %	ASTM D570
	0.58 % @Temperature 100 °C	0.58 % @Temperature 212 °F	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC method
Melt Flow	7.0 g/10 min @Load 1.20 kg, Temperature 300 °C	7.0 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	70	70	ASTM D785
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength at Break	68.0 MPa	9860 psi	50 mm/min; ASTM D638
Tensile Strength, Yield	62.0 MPa	8990 psi	50 mm/min; ASTM D638
Elongation at Break	135 %	135 %	50 mm/min; ASTM D638
Elongation at Yield	7.0 %	7.0 %	50 mm/min; ASTM D638
Flexural Yield Strength	97.0 MPa	14100 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.34 GPa	339 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	9.07 J/cm	17.0 ft-lb/in	ASTM D256
Izod Impact, Unnotched	32.04 J/cm	60.02 ft-lb/in	ASTM D4812
Tensile Impact Strength	630 kJ/m ²	300 ft-lb/in ²	ASTM D1822
Falling Dart Impact	169 J	125 ft-lb	ASTM D3029
Taber Abrasion, mg/1000 Cycles	10	10	CS-17, 1 kg; ASTM D1044

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00e+17$ ohm-cm	$\geq 1.00e+17$ ohm-cm	ASTM D257
Dielectric Constant	2.96	2.96	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	3.17	3.17	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dissipation Factor	14.9 kV/mm	378 kV/in	in air; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.00090	0.00090	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Comparative Tracking Index	0.010	0.010	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Hot Wire Ignition, HWI	250 - 400 V	250 - 400 V	UL 746A
High Amp Arc Ignition, HAI	30 - 60 sec	30 - 60 sec	UL 746A
High Voltage Arc-Tracking Rate, HVTR	60 - 120 arcs	60 - 120 arcs	UL 746A
	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	UL 746A

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	68.4 $\mu\text{m}/\text{m}\cdot\text{°C}$	38.0 $\mu\text{in}/\text{in}\cdot\text{°F}$	ASTM E831
	@Temperature -40.0 - 95.0 °C	@Temperature -40.0 - 203 °F	
Specific Heat Capacity	1.25 J/g $\cdot\text{°C}$	0.299 BTU/lb $\cdot\text{°F}$	ASTM C 351
Thermal Conductivity	0.190 W/m-K	1.32 BTU-in/hr-ft $^2\cdot\text{°F}$	ASTM C177
Deflection Temperature at 0.46 MPa (66 psi)	137 °C	279 °F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Deflection Temperature at 1.8 MPa (264 psi)	132 °C	270 °F	unannealed; ASTM D648
	@Thickness 6.40 mm	@Thickness 0.252 in	
Vicat Softening Point	154 °C	309 °F	Rate B/50; ASTM D1525
UL RTI, Electrical	130 °C	266 °F	UL 746B
UL RTI, Mechanical with Impact	130 °C	266 °F	UL 746B
UL RTI, Mechanical without Impact	130 °C	266 °F	UL 746B

Flammability, UL94 HB @Thickness 1.47 mm HB @Thickness 0.0579 in UL 94

Optical Properties	Metric	English	Comments
Refractive Index	1.586	1.586	ASTM D542
Haze	1.0 % @Thickness 2.54 mm	1.0 % @Thickness 0.100 in	ASTM D1003
Transmission, Visible	88 % @Thickness 2.54 mm	88 % @Thickness 0.100 in	ASTM D1003

Processing Properties	Metric	English	Comments
Nozzle Temperature	305 - 325 °C	581 - 617 °F	Injection Molding
Zone 1	290 - 310 °C	554 - 590 °F	
Zone 2	300 - 320 °C	572 - 608 °F	
Zone 3	310 - 330 °C	590 - 626 °F	
Melt Temperature	310 - 330 °C	590 - 626 °F	
Mold Temperature	80.0 - 115 °C	176 - 239 °F	
Drying Temperature	120 °C	248 °F	Injection Molding
Dry Time	3.00 - 4.00 hour	3.00 - 4.00 hour	Injection Molding
	48.0 hour	48.0 hour	Cumulative; Injection Molding
Moisture Content	0.020 %	0.020 %	
Back Pressure	0.300 - 0.700 MPa	43.5 - 102 psi	
Shot Size	40 - 60 %	40 - 60 %	
Vent Depth	0.00250 - 0.00760 cm	0.000984 - 0.00299 in	
Screw Speed	40 - 70 rpm	40 - 70 rpm	