

SABIC® 2202U0

SABIC® LDPE 2202U0 is an Ultra Melt Strength (UMS) grade typically used in foam applications. Application SABIC® LDPE 2202U0 can be typically used for all types of foam, produced with chemical blowing agents or physical gases, X-linked and non X-linked. This product is not intended for and must not be used in any pharmaceutical/medical applications.

Physical Properties	Metric	English	Comments
Density	0.922 g/cc	0.0333 lb/in ³	ASTM D1505

Melt Flow	1.9 g/10 min @Load 2.16 kg, Temperature 190 °C	1.9 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133
-----------	--	--	----------

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	46	46	ISO 868

Modulus of Elasticity	0.260 GPa	37.7 ksi	SABIC method
-----------------------	-----------	----------	--------------

Thermal Properties	Metric	English	Comments
Heat of Fusion	110 J/g	47.3 BTU/lb	DIN 53765

Melting Point	108 °C	226 °F	DIN 53765
---------------	--------	--------	-----------

Crystallization Temperature	97.0 °C	207 °F	DIN 53765
-----------------------------	---------	--------	-----------

Vicat Softening Point	90.0 °C	194 °F	at 10 N (VST/A); ISO 306
-----------------------	---------	--------	--------------------------